

PATENT APPLICATION
EXPRESS MAIL NO. EL774686695US
ATTORNEY'S DOCKET NO. 01-1-424
COVER SHEET

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

TITLE:

Protective Spinel Coating for Aluminate Phosphors

INVENTORS:

Madis Raukas
100 Fulton St., Apt. 5P
Boston, MA 02109

Kailash C. Mishra
107 Main St.
N. Chelmsford, MA 01863

&

Thomas H. Reilly III
420 Route 6A
East Sandwich, MA 02537

109350-8949660

Protective Spinel Coating for Aluminate Phosphors

5 TECHNICAL FIELD

This invention is related to protective coatings for phosphor particles. More particularly, this invention relates to aluminate phosphors such as barium magnesium aluminate activated by Eu^{2+} and coatings applied thereto.

10

BACKGROUND OF THE INVENTION

Common aluminate phosphors include $(\text{Ce}, \text{Tb})\text{MgAl}_{11}\text{O}_{19}:\text{Ce}^{3+}, \text{Tb}^{3+}$, $\text{Sr}_4\text{Al}_{14}\text{O}_{25}:\text{Eu}^{2+}$ and $\text{BaMgAl}_{10}\text{O}_{17}:\text{Eu}^{2+}$. Such phosphors are widely used in fluorescent lamps and more recently in electronic display devices such as plasma display panels (PDP). The ability of these phosphors to resist losing brightness during the manufacture and operation of these devices is an important consideration. For example, the brightness of the widely used blue-emitting barium magnesium aluminate phosphor, $\text{BaMgAl}_{10}\text{O}_{17}:\text{Eu}^{2+}$, (BAM) degrades during the thermal processing and operation of fluorescent lamps and PDP devices. The disproportionate decrease in the light output from the blue-emitting BAM phosphor component causes an undesirable color shift in the overall emission from these devices.

25

The thermal degradation of the phosphors during thermal processing is believed to be related to oxidation of the activator ions. In the case of BAM phosphors, oxygen atoms are believed to diffuse into the BAM phosphor to the vicinity of the Eu^{2+} ions and oxidize them. The ease with which oxygen atoms or other large ions diffuse in the BAM lattice is related to its

30

open structure in the intermediate plane between blocks of spinel-like structures. The high temperature processing of fluorescent lamps and PDP displays promotes this oxidative degradation leading to an initial loss in lumens. The radiative degradation which occurs over time in mercury-discharge lamps is believed to be primarily due to color center formation caused by mercury's energetic vacuum-ultraviolet emission at 185 nm. This causes a further decrease in lumen output from the phosphor during the operation of fluorescent lamps.

SUMMARY OF THE INVENTION

It is an object of the invention to obviate the disadvantages of the prior art.

It is another object of the invention to provide a protective coating for reducing the thermal and radiative degradation of aluminate phosphors.

It is yet another object of the invention to provide a method for applying a protective coating which is compatible with conventional fluorescent lamp manufacturing techniques.

In accordance with one object the invention, there is provided an aluminate phosphor having at least a partial spinel coating formulated to have a general formula $Mg_{1-x}Al_{2(1-y)}O_{4-3y-x}$, where $0 \leq x < 1$ and $0 \leq y < 1$.

In accordance with another object of the invention, there is provided a method of applying at least a partial spinel coating on an aluminate phosphor comprising the steps of:

(a) combining an aqueous solution of coating precursors and an aluminate phosphor, the aqueous solution formulated to yield a spinel coating having a general formula $Mg_{1-x}Al_{2(1-y)}O_{4-3y-x}$, where $0 \leq x < 1$ and $0 \leq y < 1$;

(b) drying the aqueous solution containing the phosphor; and

(c) firing the phosphor to form the at least partial coating.

DESCRIPTION OF PREFERRED EMBODIMENTS

For a better understanding of the present invention, together with other and further objects, advantages and capabilities thereof, reference is made to the following disclosure and appended claims.

We have discovered that the thermal and radiative degradation of an aluminate phosphor, in particular, the blue-emitting barium magnesium aluminate (BAM) phosphor, $BaMgAl_{10}O_{17}:Eu^{2+}$, may be controlled by applying at least a partial spinel coating on the phosphor surface. The coating is applied by an aqueous solution method which may be compatible with current fluorescent lamp manufacturing techniques. The spinel coating is formulated to have the general formula $Mg_{1-x}Al_{2(1-y)}O_{4-3y-x}$, where $0 \leq x < 1$ and $0 \leq y < 1$. In a preferred coating composition, the values for x and y are $x=0$ and $0 \leq y \leq 2/3$. More preferably, x is 0 and y is about 0.5.

The spinel coating of this invention is believed to provide a diffusion barrier which reduces the oxidation of the activator ions. Known oxygen diffusion coefficients in materials having a

β -alumina structure indicate that it is more difficult for oxygen ions to move through the spinel layers of β -alumina compared to diffusion along the intermediate planes of the material.

Furthermore, the spinel coating contains ions already present in some aluminate phosphors, particularly BAM. As a result, the diffusion of these ions (or its significance) between the bulk phosphor and the coating during the coating process may be reduced compared to phosphors lacking aluminum and magnesium ions. Ideal spinel, MgAl_2O_4 is known to be transparent to the primary 254 nm UV radiation from a mercury discharge and has a relatively dense anion packing. The transparency of the spinel coating of this invention to 254 nm radiation allows the underlying phosphor to be excited by the primary UV radiation from the Hg-discharge. Furthermore, the ternary spinel composition may be varied over a wide range in order to tailor the properties of protective coating for the specific aluminate phosphor.

In a general method, the spinel coating of this invention is applied by combining the aluminate phosphor with an aqueous solution of the coating precursors which is formulated to yield the desired coating composition. The solution is then dried and the phosphor is fired to form the coating. In a preferred method, the coating precursors are nitrates and the dried phosphor is first fired in air at a lower temperature (preferably, 600°C for 30 mins) to remove the nitrate groups and then in a reducing atmosphere at a higher temperature (preferably, 1200°C for 90 mins). In a more preferred method, the nitrates are dissolved into a minimum amount of water at about 90°C, stirred and finally mixed with the phosphor powder in a 10% or higher weight ratio. The slurried phosphor is

5

10

DATE	TIME	LOCATION	WIND	TEMP	SEA	REMARKS
1965	0800	1000	10	20	1	1000
1965	0900	1000	10	20	1	1000
1965	1000	1000	10	20	1	1000
1965	1100	1000	10	20	1	1000
1965	1200	1000	10	20	1	1000
1965	1300	1000	10	20	1	1000
1965	1400	1000	10	20	1	1000
1965	1500	1000	10	20	1	1000
1965	1600	1000	10	20	1	1000
1965	1700	1000	10	20	1	1000
1965	1800	1000	10	20	1	1000
1965	1900	1000	10	20	1	1000
1965	2000	1000	10	20	1	1000
1965	2100	1000	10	20	1	1000
1965	2200	1000	10	20	1	1000
1965	2300	1000	10	20	1	1000
1965	0000	1000	10	20	1	1000
1965	0100	1000	10	20	1	1000
1965	0200	1000	10	20	1	1000
1965	0300	1000	10	20	1	1000
1965	0400	1000	10	20	1	1000
1965	0500	1000	10	20	1	1000
1965	0600	1000	10	20	1	1000
1965	0700	1000	10	20	1	1000
1965	0800	1000	10	20	1	1000
1965	0900	1000	10	20	1	1000
1965	1000	1000	10	20	1	1000
1965	1100	1000	10	20	1	1000
1965	1200	1000	10	20	1	1000
1965	1300	1000	10	20	1	1000
1965	1400	1000	10	20	1	1000
1965	1500	1000	10	20	1	1000
1965	1600	1000	10	20	1	1000
1965	1700	1000	10	20	1	1000
1965	1800	1000	10	20	1	1000
1965	1900	1000	10	20	1	1000
1965	2000	1000	10	20	1	1000
1965	2100	1000	10	20	1	1000
1965	2200	1000	10	20	1	1000
1965	2300	1000	10	20	1	1000
1965	0000	1000	10	20	1	1000
1965	0100	1000	10	20	1	1000
1965	0200	1000	10	20	1	1000
1965	0300	1000	10	20	1	1000
1965	0400	1000	10	20	1	1000
1965	0500	1000	10	20	1	1000
1965	0600	1000	10	20	1	1000
1965	0700	1000	10	20	1	1000
1965	0800	1000	10	20	1	1000
1965	0900	1000	10	20	1	1000
1965	1000	1000	10	20	1	1000
1965	1100	1000	10	20	1	1000
1965	1200	1000	10	20	1	1000
1965	1300	1000	10	20	1	1000
1965	1400	1000	10	20	1	1000
1965	1500	1000	10	20	1	1000
1965	1600	1000	10	20	1	1000
1965	1700	1000				

20

25

Samples before and after final firing were analyzed using x-ray diffraction (XRD), x-ray photoelectron spectroscopy (XPS), scanning electron microscopy (SEM) techniques and by optical spectroscopy. XRD data indicate clearly the formation of the spinel phase in addition to the BAM diffraction pattern. The results from the XPS analysis show the signal from barium being reduced by 30% whereas the reduction in europium signal is nearly 70% in addition to a substantial increase in signal from magnesium. An enhancement of the magnesium to aluminum ratio on the surface from the observed value of 0.01 (for BAM) to about 0.03 indicates at least a partial spinel coating was formed on the surface of the phosphor particles.

Approximately, half of each of the coated samples was heated to 600°C for 30 minutes in air, together with an uncoated control sample. Luminescence from the samples was measured in a SPEX Fluorolog- 2 spectrometer under 254 nm excitation. The brightness results are given in Table 1 in terms of the relative integrated radiance of the Eu^{2+} emission band around 450 nm. The application of the spinel coating reduces the initial brightness of the phosphor by 10% but protects the phosphor from degrading further. The brightness of coated BAM phosphor is at least about 10% greater compared to the uncoated sample after the heat treatment. Emission spectra of the samples show no changes in the emission curves of the coated phosphors relative to the uncoated phosphor.

Table 1

Sample	Relative integrated radiance	
	before heat treatment	after 30 min at 600°C air
uncoated	1.00	0.68
coated	0.90	0.76

- 5 These results demonstrate the use of a spinel coating as a protective layer against the oxidative degradation of BAM phosphors.

EXAMPLE 2

10 The slow radiative degradation of BAM in Hg-discharge lamps can be simulated by a rapid test using radiation from an excimer laser source at about 190 nm (e.g., 193 nm ArF excimer radiation). After being irradiated for 4.5 hours at the power density of 7.5W/cm², the coated BAM phosphor sample retained 65% of its initial emission under 254 nm excitation compared to 45% for an uncoated phosphor sample. Thus, the spinel-coated phosphor may retain more than about 50%, and preferably more than about 60%, of its initial brightness under these severe
20 conditions. This demonstrates a significant reduction in the radiative degradation of the europium-activated BAM.

While there has been shown and described what are at the present considered the preferred embodiments of the invention, it will
25 be obvious to those skilled in the art that various changes and

EXPRESS MAIL NO. EL774686695US
DOCKET NO. 01-1-424

PATENT

modifications may be made therein without departing from the
scope of the invention as defined by the appended claims.

0964060 0964060